


BS 476: Part 6: 1989+A1:2009



Method Of Test For Fire Propagation For Products

A Report To: Solomon & Wu t/a Foresso

Document Reference: 438199

Date: 4th March 2021

Issue No.: 1

Page 1



0249

Executive Summary

Objective To determine the performance of the following product when tested in accordance with BS 476: Part 6: 1989+A1: 2009.

Generic Description	Product reference	Thickness	Weight per unit area or density
Coated plywood	"Foresso"	24mm	21kg/m ²
Individual components used to manufacture composite:			
Coating	"Foresso"	6mm	Unable to provide
Birch plywood	"FSC LVA RigaPLYBB/BB birch plywood"	18mm	13kg/m ²
Please see page 5 of this test report for the full description of the product tested			

Test Sponsor Solomon & Wu t/a Foresso, Unit Q1, Hawthorns Industrial Estate, Middlemore Road, Birmingham, West Midlands, B21 0BH


Test Results:


Fire propagation index, I	=	19.3
Sub index, i ₁	=	2.0
Sub index, i ₂	=	13.2
Sub index, i ₃	=	4.0

An uncertainty of measurement estimation has been conducted in relation to the fire propagation index, I and the sub index, i₁. The findings are as detailed in Annex A of this report.

Date of Test 23rd and 24th February 2021

Signatories


Responsible Officer H. Harper * Testing Officer


Authorised C. Jacques * Senior Technical Officer

* For and on behalf of [Warringtonfire](#).

Report Issued: 4 th March 2021

This version of the report has been produced from a .pdf format electronic file that has been provided by [Warringtonfire](#) to the sponsor of the report and must only be reproduced in full. Extracts or abridgements of reports must not be published without permission of [Warringtonfire](#).

Document No.:	438199	Page No.:	2 of 11
Author:	H. Harper	Issue Date:	4 th March 2021
Client:	Solomon & Wu t/a Foresso	Issue No.:	1



0249

CONTENTS	PAGE NO.
EXECUTIVE SUMMARY	2
SIGNATORIES.....	2
TEST DETAILS.....	4
DESCRIPTION OF TEST SPECIMENS.....	5
TEST RESULTS	6
TABLE 1.....	7
TABLE 2.....	8
TABLE 3.....	9
ANNEX A	10
REVISION HISTORY	11



Test Details

Purpose of test	<p>To determine the performance of a product when it is subjected to the conditions of the test specified in BS 476: Part 6: 1989+A1: 2009, "Fire tests on building materials and structures, method for fire propagation for products".</p> <p>The test was performed in accordance with the procedure specified in BS 476: Part 6: 1989+A1: 2009, and this report should be read in conjunction with that British Standard.</p>
Scope of test	<p>BS 476: Part 6: 1989+A1: 2009 specifies a method of test, the result being expressed as a fire propagation index, that provides a comparative measure of the contribution to the growth of fire made by an essentially flat material, composite or assembly. It is primarily intended for the assessment of the performance of internal wall and ceiling linings.</p>
Fire test study group/EGOLF	<p>Certain aspects of some fire test specifications are open to different interpretations. The Fire Test Study Group and EGOLF have identified a number of such areas and have agreed Resolutions which define common agreement of interpretations between fire test laboratories which are members of the Groups. Where such Resolutions are applicable to this test they have been followed.</p>
Instruction to test	<p>The test was conducted on the 23rd and 24th February 2021 at the request of Solomon & Wu t/a Foresso, the sponsor of the test.</p>
Provision of test specimens	<p>The specimens were supplied by the sponsor of the test. Warringtonfire was not involved in any selection or sampling procedure. The results stated in this report apply to the samples as received.</p>
Conditioning of specimens	<p>The specimens for testing to BS 476: Part 6: 1989+A1: 2009 together with the specimens for testing to BS 476: Part 7: 1997 were received on the 3rd February 2021.</p> <p>Prior to the tests, all of the specimens were conditioned to constant mass at a temperature of $23 \pm 2^{\circ}\text{C}$ and a relative humidity of $50 \pm 5\%$. One specimen from the total sample submitted for test was selected for constant mass verification.</p>
Form in which the specimens were tested	<p>Composite - Combination of materials which are generally recognised in building constructions as discrete entities e.g. coated or laminated materials.</p>
Exposed face	<p>The decorative face of the specimens was exposed to the heating conditions of the test.</p>

Document No.:	438199	Page No.:	4 of 11
Author:	H. Harper	Issue Date:	4 th March 2021
Client:	Solomon & Wu t/a Foresso	Issue No.:	1



0249

Description of Test Specimens

The description of the specimens given below has been prepared from information provided by the sponsor of the test. This information has not been independently verified by [Warringtonfire](#). All values quoted are nominal, unless tolerances are given.

General description		Coated plywood
Product reference of coating system		"Foresso"
Name of manufacturer		Solomon & Wu Ltd t/a Foresso
Overall thickness		24mm (stated by sponsor) 22.23mm (determined by Warringtonfire)
Overall weight per unit area		21kg/m ² (stated by sponsor) 23.34kg/m ² (determined by Warringtonfire)
Final coating product (Test face)	Generic type	See Note 1 Below
	Product reference	"Foresso"
	Name of manufacturer	Solomon & Wu Ltd t/a Foresso
	Colour reference	"Charcoal"
	Colour	Black
	Number of coats	1
	Application thickness	6mm
	Weight per unit area	See Note 1 Below
	Application method	Cold cast
	Flame retardant details	See Note 2 Below
	Curing process	Ambient temperature cure
Substrate	Generic type	Birch throughout plywood
	Product reference	"FSC LVA RigaPLY BB/BB birch plywood"
	Name of manufacturer	Latvijas Finieris
	Thickness	18mm
	Weight per unit area	13kg/m ²
	Flame retardant details	See Note 2 Below
Brief description of manufacturing process of coatings		See Note 3 Below

Note 1: The sponsor was unable to provide this information.

Note 2: The sponsor of the test has confirmed that no flame retardant additives were utilised in the production of the component.

Note 3: The sponsor of the test has provided this information but at the specific request of the sponsor, these details have been omitted from the report and are instead held on the confidential file relating to this investigation.

Test Results

Results

A total of three specimens were tested. The laboratory record sheet relating to each of the test specimens is appended to this report (refer to Tables 1, 2 and 3).

Throughout the test on each specimen careful observation was made of the product's behaviour within the apparatus and special note was taken of any of the phenomena listed in clause 9.2 of the Standard. None of the listed phenomena was observed and the test results on all three specimens tested were valid.

The following test results were obtained for the product.

Fire propagation index, I	=	19.3
Sub index, i_1	=	2.0
Sub index, i_2	=	13.2
Sub index, i_3	=	4.0

An uncertainty of measurement estimation has been conducted in relation to the fire propagation index, I and the sub index, i_1 . The findings are as detailed in Annex A of this report.

NOTE: If a suffix 'R' is included in the above fire propagation index, I, then this indicates that the results should be treated with caution.

Applicability of test result

The test results relate only to the behaviour of the test specimens of the product under the particular conditions of test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

The test results relate only to the specimens of the product in the form in which they were tested. Small differences in the composition or thickness of the product may significantly affect the performance during the test and may therefore invalidate the test results. Care should be taken to ensure that any product which is supplied or used is fully represented by the specimens which were tested.

Validity

The specification and interpretation of fire test methods are the subject of ongoing development and refinement. Changes in associated legislation may also occur. For these reasons it is recommended that the relevance of test reports over five years old should be considered by the user. The laboratory that issued the report will be able to offer, on behalf of the legal owner, a review of the procedures adopted for a particular test to ensure that they are consistent with current practices, and if required may endorse the test report.

This report may only be reproduced in full. Extracts or abridgements shall not be published without permission of [Warringtonfire](#).

Document No.:	438199	Page No.:	6 of 11
Author:	H. Harper	Issue Date:	4 th March 2021
Client:	Solomon & Wu t/a Foresso	Issue No.:	1



0249

Table 1

Laboratory Record Sheet**FIRE PROPAGATION TEST - BS476:PART 6:1989+A1:2009**

Specimen No. : 1

Date : 23-Feb-21

Time mins t	Specimen Temperature Deg C Ts	Calibration Temperature Deg C Tc	Ts- Tc/10t	Sub Index Of Performance
0.50	14	14	0.00	
1.00	32	20	1.20	
1.50	43	25	1.20	
2.00	46	29	0.85	
2.50	51	33	0.72	
3.00	60	37	0.77	4.74
4.00	157	70	2.18	
5.00	279	109	3.40	
6.00	299	139	2.67	
7.00	307	161	2.09	
8.00	317	178	1.74	
9.00	322	192	1.44	
10.00	327	203	1.24	14.75
12.00	329	221	0.90	
14.00	352	231	0.86	
16.00	356	241	0.72	
18.00	336	251	0.47	
20.00	325	256	0.35	3.30
Total Index of Performance S			=	22.79

SubIndex s1 4.74

SubIndex s2 14.75

SubIndex s3 3.30

Index of Performance S 22.79

Document No.: 438199

Page No.: 7 of 11

Author: H. Harper

Issue Date: 4th March 2021

Client: Solomon & Wu t/a Foresso

Issue No.: 1



0249

Table 2

Laboratory Record Sheet**FIRE PROPAGATION TEST - BS476:PART 6:1989+A1:2009**

Specimen No. : 2

Date : 23-Feb-21

Time mins t	Specimen Temperature Deg C Ts	Calibration Temperature Deg C Tc	Ts- Tc/10t	Sub Index Of Performance
0.50	13	14	0.00	
1.00	17	20	0.00	
1.50	25	25	0.00	
2.00	33	29	0.20	
2.50	36	33	0.12	
3.00	44	37	0.23	0.55
4.00	110	70	1.00	
5.00	236	109	2.54	
6.00	284	139	2.42	
7.00	309	161	2.11	
8.00	324	178	1.83	
9.00	334	192	1.58	
10.00	341	203	1.38	12.85
12.00	352	221	1.09	
14.00	371	231	1.00	
16.00	384	241	0.89	
18.00	375	251	0.69	
20.00	373	256	0.59	4.26
Total Index of Performance S			=	17.67

SubIndex s1 0.55

SubIndex s2 12.85

SubIndex s3 4.26

Index of Performance S 17.67

Document No.: 438199

Page No.: 8 of 11

Author: H. Harper

Issue Date: 4th March 2021

Client: Solomon & Wu t/a Foresso

Issue No.: 1



0249

Table 3

Laboratory Record Sheet**FIRE PROPAGATION TEST - BS476:PART 6:1989+A1:2009**

Specimen No. : 3

Date : 24-Feb-21

Time mins t	Specimen Temperature Deg C Ts	Calibration Temperature Deg C Tc	Ts- Tc/10t	Sub Index Of Performance
0.50	11	14	0.00	
1.00	19	20	0.00	
1.50	26	25	0.07	
2.00	32	29	0.15	
2.50	39	33	0.24	
3.00	45	37	0.27	0.72
4.00	108	70	0.95	
5.00	220	109	2.22	
6.00	276	139	2.28	
7.00	302	161	2.01	
8.00	320	178	1.78	
9.00	341	192	1.66	
10.00	324	203	1.21	12.11
12.00	361	221	1.17	
14.00	368	231	0.98	
16.00	388	241	0.92	
18.00	393	251	0.79	
20.00	390	256	0.67	4.52
Total Index of Performance S			=	17.35

SubIndex s1 0.72

SubIndex s2 12.11

SubIndex s3 4.52

Index of Performance S 17.35

Document No.: 438199

Page No.: 9 of 11

Author: H. Harper

Issue Date: 4th March 2021

Client: Solomon & Wu t/a Foresso

Issue No.: 1



0249

Annex A

Uncertainty of measurement

Specimen No.	1	2	3	Average
Fire propagation index, I	+0.77	+0.54	+0.40	+0.57
	-0.46	-0.26	-0.27	-0.33
Sub index i_1	+0.76	+0.52	+0.37	+0.55
	-0.44	-0.22	-0.27	-0.30

The reported expanded uncertainty is based on a standard uncertainty multiplied by a coverage factor $k=2$, providing a coverage probability of approximately 95%. The uncertainty evaluation has been carried out in accordance with UKAS requirements.

Document No.: 438199

Page No.: 10 of 11

Author: H. Harper

Issue Date: 4th March 2021

Client: Solomon & Wu t/a Foresso

Issue No.: 1



0249

Revision History

Issue No :	Re-issue Date:
Revised By:	Approved By:
Reason for Revision:	

Issue No :	Re-issue Date:
Revised By:	Approved By:
Reason for Revision:	